



Design and Performance Optimizations of Advanced Erosion-Resistant Low Conductivity Thermal Barrier Coatings for Rotorcraft Engines

*Dongming Zhu, Robert A. Miller, and Maria A. Kuczmarski
Glenn Research Center, Cleveland, Ohio*

NASA STI Program . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) program plays a key part in helping NASA maintain this important role.

The NASA STI Program operates under the auspices of the Agency Chief Information Officer. It collects, organizes, provides for archiving, and disseminates NASA's STI. The NASA STI program provides access to the NASA Aeronautics and Space Database and its public interface, the NASA Technical Reports Server, thus providing one of the largest collections of aeronautical and space science STI in the world. Results are published in both non-NASA channels and by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services also include creating custom thesauri, building customized databases, organizing and publishing research results.

For more information about the NASA STI program, see the following:

- Access the NASA STI program home page at <http://www.sti.nasa.gov>
- E-mail your question via the Internet to help@sti.nasa.gov
- Fax your question to the NASA STI Help Desk at 443-757-5803
- Telephone the NASA STI Help Desk at 443-757-5802
- Write to:
NASA Center for AeroSpace Information (CASI)
7115 Standard Drive
Hanover, MD 21076-1320



Design and Performance Optimizations of Advanced Erosion-Resistant Low Conductivity Thermal Barrier Coatings for Rotorcraft Engines

*Dongming Zhu, Robert A. Miller, and Maria A. Kuczmarski
Glenn Research Center, Cleveland, Ohio*

Prepared for the
66th Annual Forum and Technology Display (AHS Forum 66)
sponsored by the American Helicopter Society
Phoenix, Arizona, May 11–13, 2010

National Aeronautics and
Space Administration

Glenn Research Center
Cleveland, Ohio 44135

Acknowledgments

The work was supported by NASA Fundamental Aeronautics Program (FAP) Subsonic Rotary Wing (SRW) project.
The authors are grateful to Mr. Michael Perez for performing the burner rig erosion tests.

This work was sponsored by the Fundamental Aeronautics Program
at the NASA Glenn Research Center.

Level of Review: This material has been technically reviewed by technical management.

Available from

NASA Center for Aerospace Information
7115 Standard Drive
Hanover, MD 21076-1320

National Technical Information Service
5301 Shawnee Road
Alexandria, VA 22312

Available electronically at <http://www.sti.nasa.gov>

Design and Performance Optimizations of Advanced Erosion-Resistant Low Conductivity Thermal Barrier Coatings for Rotorcraft Engines

Dongming Zhu, Robert A. Miller, and Maria A. Kuczmarski
National Aeronautics and Space Administration
Glenn Research Center
Cleveland, Ohio 44135

Abstract

Thermal barrier coatings will be more aggressively designed to protect gas turbine engine hot-section components in order to meet future rotorcraft engine higher fuel efficiency and lower emission goals. For thermal barrier coatings designed for rotorcraft turbine airfoil applications, further improved erosion and impact resistance are crucial for engine performance and durability, because the rotorcraft are often operated in the most severe sand erosive environments. Advanced low thermal conductivity and erosion-resistant thermal barrier coatings are being developed, with the current emphasis being placed on thermal barrier coating toughness improvements using multi-component alloying and processing optimization approaches. The performance of the advanced thermal barrier coatings has been evaluated in a high temperature erosion burner rig and a laser heat-flux rig to simulate engine erosion and thermal gradient environments. The results have shown that the coating composition and architecture optimizations can effectively improve the erosion and impact resistance of the coating systems, while maintaining low thermal conductivity and cyclic oxidation durability.

Introduction

Advanced thermal barrier coatings (TBCs) are critical for designing next generation rotorcraft turbine engines because of their ability to allow increased engine gas temperatures and reduced cooling requirements, thus helping to achieve improved engine performance and durability (Refs. 1 to 5). It has been shown that advanced turbine thermal barrier coatings can provide significant benefits in increasing engine efficiency (Ref. 5). Advanced hot-section material technology is especially critical in improving the turboshaft based rotorcraft engine performance, and a more nearly prime-reliant coating design approach is necessary to take full advantage of the thermal barrier coating technology in future rotorcraft engine systems. Turbine blade thermal barrier coatings are especially susceptible to engine ingested sand erosion and impact damage because of the high velocity flow path nature of the blades and complex particulate-coating interactions under high heat-flux combustion turbine environments. The NASA Rotary Wing Project has been addressing low thermal conductivity, high toughness and erosion resistant turbine

blade thermal barrier coating development based on nano-tetragonal phase toughening design approaches (Refs. 6 to 8).

The main objective of this current effort is to evaluate and optimize the processing of advanced turbine blade thermal barrier coating systems with increased erosion and impact resistance for rotorcraft propulsion engines. The high temperature erosion performance of the turbine TBC systems will be discussed. Thermal conductivity and thermal cyclic durability of the coating systems have been evaluated. The emphasis is particularly placed on the multi-component alloying and processing optimization for the erosion resistance and the combined oxidation and erosion effects, helping understand the complex erosion mechanisms for developing comprehensive turbine blade TBC life prediction models.

Experimental Procedures

Advanced Thermal Barrier Coatings

Advanced turbine thermal barrier coatings were designed using a multi-component defect-clustering approach and processed using an Electron Beam-Physical Vapor Deposition (EB-PVD) technique (Refs. 1 to 3). Although the high temperature multi-component turbine thermal barrier coatings have included pseudo-four component $\text{ZrO}_2\text{-Y}_2\text{O}_3\text{-Gd}_2\text{O}_3\text{-Yb}_2\text{O}_3$ (t' ZrYGdYb) and pseudo-six component $\text{ZrO}_2\text{-Y}_2\text{O}_3\text{-Gd}_2\text{O}_3\text{-Yb}_2\text{O}_3\text{-TiO}_2\text{-Ta}_2\text{O}_5$ (t' ZrYGdYbTT) systems, the present study is primarily focused on the four component systems because of the less complex and better controlled EB-PVD processing parameters. The EB-PVD coatings were processed at a vendor, and four processing conditions were used in the EB-PVD process by varying electron beam power, chamber pressure, and specimen deposition temperature. The advanced TBC systems, typically consisting of a 130 to 200 μm thick ceramic top coat and a 75 to 100 μm thick PtAl intermediate bond coat, were electron beam-physical vapor deposited (EB-PVD) on to 25.4 mm diameter disks of Rene N5 nickel-base superalloy substrates. The EB-PVD coatings were all deposited using pre-fabricated evaporation ingots made using the designed compositions.

A Mach 0.3 to 1.0 high velocity burner rig with erosion capability was developed for the turbine blade thermal barrier coating erosion testing in a laboratory simulated turbine engine relevant environments (Ref. 8). Computational Fluid Dynamics (CFD) modeling and experimental testing were

systematically studied in the high burner velocities ranging from Mach 0.3 to 0.9, representative to turbine engine conditions. In the present study, Al_2O_3 particles were used as erodent, as similarly reported in previous work by others (Refs. 9 and 10). The nominal particle sizes used were ranged from 27 to 100 μm . The coating erosion testing was primarily conducted at 2000 °F. However, comparisons have been made for erosion tests performed at 1800 to 2200 °F. The set of the process optimization coatings were also pre-cyclically oxidized in a furnace for 128 and 256 hr at 2025 °F in 2 hr hot time cycles, and then burner erosion tested at high temperature to investigate the pre-exposure cyclic oxidation effect. In all cases, the erosion rates were determined by the erodent amount required for the coating erosion recession and coating breakthrough. A more sophisticated characterization of three-dimensional erosion surfaces and erosion behavior of thermal barrier coating systems under complexity of erosion burner conditions will be reported at a later time.

Thermal conductivity and cyclic durability tests were also conducted using the high heat flux laser test rig and cyclic furnaces at typical operating relevant temperatures, and experiment details will be discussed elsewhere (Ref. 11). The advanced t' coatings were also compared with the baseline ZrO_2 -7wt% Y_2O_3 (7YSZ) in the performance.

Experimental Results and Discussion

Thermal Conductivity

Figure 1 shows the thermal conductivity of four-component ZrO_2 - Y_2O_3 - Gd_2O_3 - Yb_2O_3 and six-component low conductivity ZrO_2 - Y_2O_3 - Gd_2O_3 - Yb_2O_3 - TiO_2 - Ta_2O_5 coatings, tested at 2400 °F (1316 °C) using a steady-state laser heat flux rig. The four-component turbine coatings have lower thermal conductivity than the baseline 7YSZ (a yttria partially stabilized zirconia) coating, but higher conductivity than the combustor application oriented cubic-phase thermal barrier coatings and the currently less developed six-component coating systems. The four-component turbine TBCs have been developed with toughness enhancements to improve the erosion resistance required by the turbine airfoil applications. The composition and phase optimization also have ensured the basic erosion resistance requirements of the coating systems.

Figure 2 shows the furnace cyclic life comparisons of the four-component and six-component low k coatings. The coating cyclic life was optimized for a highly stable tetragonal t' phase among the different coating systems. It can be seen that the four-component coatings have an optimum durability with lower total Rare Earth (RE) oxide dopant (RE_2O_3) concentrations similar to the baseline 7YSZ, with the cyclic life of 300 to 400 hr at 2125 °F (1163 °C), as compared to the six-component coating systems having additional Ti and Ta additions. The Ti and Ta in the six component systems have the advantages of allowing increased rare earth dopants while still maintaining t' phase and lower thermal conductivities.

However, the lower dopant concentration and less complexity of the four-component systems helped the initial EB-PVD processing optimizations where the homogenization and precise control of the coating compositions are highly critical.




Figure 1.—Thermal conductivity of four-component ZrO_2 - Y_2O_3 - Gd_2O_3 - Yb_2O_3 and six-component low conductivity ZrO_2 - Y_2O_3 - Gd_2O_3 - Yb_2O_3 - TiO_2 - Ta_2O_5 coatings, tested at 2400 °F (1316 °C) using a steady-state laser heat flux rig. The four-component turbine coatings have lower thermal conductivity than the baseline 7YSZ coating, but higher conductivity than the combustor cubic phase thermal barrier coatings.




Figure 2.—Furnace cyclic life comparisons of four-component ZrO_2 - Y_2O_3 - Gd_2O_3 - Yb_2O_3 and six-component low conductivity ZrO_2 - Y_2O_3 - Gd_2O_3 - Yb_2O_3 - TiO_2 - Ta_2O_5 coatings. The cyclic life is optimized for a highly stable tetragonal t' phase for the different coating systems. The four-component coatings have an optimum life of 300 to 400 hr at 2125 °F (1163 °C), with lower total rare earth oxide (RE_2O_3) dopants as compared to the six-component coating systems with Ti and Ta additions.

Erosion Resistance

Figure 3 shows erosion behavior of a $\text{ZrO}_2\text{-2mol\%Y}_2\text{O}_3\text{-1.5mol\%Gd}_2\text{O}_3\text{-1.5mol\%Yb}_2\text{O}_3$ thermal barrier coating at high temperature using the EB-PVD process optimization experiment. The coatings were tested in the erosion burner rig under Mach 0.5 conditions at the specimen temperature of 2000 °F. The Process 1 was the baseline process condition which is the same as the standard process for the 7YSZ coating and optimized for the baseline coating. The Process 2 and 3 resulted in somewhat decreased erosion resistance of the coating systems due to the less optimized coating columnar architectures and higher porosity levels. The Process 4, however, showed quite significant, approximately 30 percent erosion resistance improvements as compared to the baseline coating.

The TBC surface morphologies of process optimization specimens were examined using a Field Emission Gun-Scanning Electron Microscope (FEG-SEM), as shown in Figure 4. It can be seen that the specimens with the standard processing (Process 1) had relatively large and uniform columnar grains (~10 to 20 μm in size). However, the TBC specimens with best optimized processing (Process 4) had finer columnar structures (~10 μm in size), and with additional much finer smaller columns (2 to 5 μm in size). The smaller column sized coatings would expect to offer higher strength and significantly improved coating strain tolerance

for improved erosion/impact resistance based on the previous erosion modeling work (Ref. 8), and also potentially providing improved furnace cyclic life durability.




Figure 3.—High temperature erosion behavior of an optimization runs of low conductivity thermal barrier coatings. The optimized process 4 of the low conductivity thermal barrier coating showed improvements in erosion resistance due to better optimized columnar microstructures.




Figure 4.—The FEG-SEM surface morphologies of turbine EB-PVD thermal barrier coatings under different process conditions. (a) Standard Process 1 condition; (b) Optimized Process 2 condition.

Cyclic Oxidation Pre-Exposure on Erosion Resistance

Figure 5 shows the pre-cyclic oxidation effect on the erosion resistance of the turbine EB-PVD thermal barrier coatings. It can be seen that in most cases, the pre-cyclic oxidation under the moderate temperature (2025°F) and times (below 300 hr) seemed to increase the erosion resistance as compared to the as processed conditions. It is speculated that the cyclic exposure has moderate sintering effects which may strengthen the coating systems. Also the pre-cyclic exposure may induce certain degrees of the interface roughening as often observed, which can further strengthen the TBC/metal bond coat interface and reduce the coating spallation under the high velocity erosion/impact testing. More systematic studies are underway to further understand the oxidation and erosion behavior and to help the development of coating life prediction models.

Figure 6 shows the erosion and oxidation based failure map under turbine testing conditions. The effect of temperature on the turbine coating erosion and oxidation life is also clearly illustrated. It can be seen that in the oxidation-based failure, the coating life is exponentially reduced with increasing temperature (\ln life in hours vs. $1/T$), because interface damage effects are significantly increased from the accelerated oxide scale growth and increased cyclic stress-temperature amplitudes during the cycling. In contrast, the erosion-based coating failure life is generally increased with temperature because the coating toughness and plasticity increase with temperature. Therefore, one can expect that in the lower temperature regime, when coating erosion is the life limiting factor, the coating would generally fail by an erosion mechanism given sufficient erodent is present, as is frequently the case in rotorcraft operating environments. On the other hand, in the higher temperature regime, when coating oxidation is the life-limiting factor, the coating would predominantly fail by an oxidation mechanism. Under very high-temperature combined erosion and oxidation conditions (2100 to 2200 °F), significantly reduced coating life was observed in the burner erosion rig tests, and has been characterized as an oxidation-erosion mechanism as shown in Figure 6. In addition to the oxidation erosion interactions, the significant softening of the baseline 7YSZ thermal barrier coating may also have contributed to the accelerated erosion failure. The coating strain-based approaches are also being developed for turbine thermal barrier coating life predictions and will be reported in future publications.

Concluding Remarks

Advanced t' phase rare earth oxide (Gd_2O_3 and Yb_2O_3 co-doped)- and TiO_2/Ta_2O_5 -alloyed, ZrO_2 -based thermal barrier coatings were designed and processed. The turbine thermal barrier coatings were developed for rotorcraft turbine engine applications, aimed at combined low conductivity and high




Figure 5.—The pre-cyclic oxidation effect on erosion resistance of EB-PVD thermal barrier coatings. The coatings were compared with the as processed, 128 hr oxidation, and 256 hr oxidation and at 2025 °F. The erosion was tested at 2000 °F. The results showed that the pre-cyclic oxidation seemed to increase the coating resistance to erosion.




Figure 6.—The erosion and oxidation based failure map under turbine testing conditions.

toughness for improved thermal barrier performance and erosion resistance. The coating thermal conductivity, cyclic durability, and erosion resistance have been optimized from composition, phase, and processing as well as microstructure optimizations. Combined erosion and oxidation life prediction approaches based on the failure maps were also illustrated.

References

1. Dongming Zhu, and Robert A. Miller, "Low Conductivity and Sintering Resistant Thermal Barrier Coatings," U.S. Patent No. 6,812,176, 2004; U.S. Patent No. 7,001,859, 2006; U.S. Patent No. 7,186,466, 2007.
2. Dongming Zhu, and Robert A. Miller, "Thermal Conductivity and Sintering Behavior of Advanced Thermal Barrier Coatings," *Ceram. Eng. Sci. Proc.*, Vol. 23 (2002), pp. 457–468.
3. Dongming Zhu and Robert A. Miller, "Development of Advanced Low Conductivity Thermal Barrier Coatings," *International Journal of Applied Ceramic Technology*, Vol. 1 (2004), pp. 86–94.
4. Dongming Zhu et al, "Thermal and Environmental Barrier Coating Development for Advanced Propulsion Engine Systems," AIAA-2007-2130, 48th AIAA/ASME/ASCE/ AHS/ASC Structures, Structural Dynamics, and Materials Conference, 23–26 Apr. 2007, Honolulu, HI.
5. Michael T. Tong, Scott M. Jones and Philip C. Arcara, Jr., "A Probabilistic Assessment of NASA Ultra-Efficient Engine Technologies for a Large Subsonic Transport," *Proceedings of Turbo Expo 2004*, GT2004-53485.
6. Dongming Zhu and Robert A. Miller, "Low conductivity and high toughness tetragonal phase structured ceramic thermal barrier coatings," U.S. Provisional Patent Application No. 60/712,613, 2005. U.S. Patent No. 7,700,508, 2010.
7. Dongming Zhu, Maria A. Kuczmarski, Robert A. Miller, and Michael D. Cuy, "Evaluation of Erosion Resistance of Advanced Turbine Thermal Barrier Coatings," *The 31st International Cocoa Beach Conference & Exposition on Advanced Ceramics & Composites*, Daytona Beach, FL, Jan. 22–26, 2007.
8. Dongming Zhu, Robert A. Miller, and Maria A. Kuczmarski, "Development and Life Prediction of Erosion Resistant Turbine Low Conductivity Thermal Barrier Coatings," *65th AHS International Annual Forum Proceedings*, v 2, p 1088–1094, 2009.
9. Robert F. Handschuh, "High Temperature Erosion of Plasma-Sprayed Yttria-Stabilized Zirconia in a Simulated Turbine Environment," NASA TP-2406; AVSCOM TR-84-C-17, Dec. 1984. Also AIAA-85-1219.
10. Robert W. Bruce, et al., "Development of 1232°C (2250°F) erosion and impact tests for thermal barrier coatings," *Tribology Transactions*, Vol. 44 (1998), 3990410.
11. Dongming Zhu, Robert A. Miller, and James L. Smialek, "Ionic Transport and Durability of Advanced Thermal Barrier Coatings," *8th Spring Meeting of the International Society of Electrochemistry Advances in Corrosion Science for Lifetime Prediction and Sustainability: A Celebration of the 100th Birthday of Mars Fontana*, May 2–5, 2010, Columbus, OH.

| REPORT DOCUMENTATION PAGE | | | | Form Approved OMB No. 0704-0188 | |
|--|------------------|--|---|---|---|
| <p>The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.</p> <p>PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.</p> | | | | | |
| 1. REPORT DATE (DD-MM-YYYY) 01-05-2012 | | 2. REPORT TYPE Technical Memorandum | | 3. DATES COVERED (From - To) | |
| 4. TITLE AND SUBTITLE Design and Performance Optimizations of Advanced Erosion-Resistant Low Conductivity Thermal Barrier Coatings for Rotorcraft Engines | | | | 5a. CONTRACT NUMBER | |
| | | | | 5b. GRANT NUMBER | |
| | | | | 5c. PROGRAM ELEMENT NUMBER | |
| 6. AUTHOR(S) Zhu, Dongming; Miller, Robert, A.; Kuczmarski, Maria, A. | | | | 5d. PROJECT NUMBER | |
| | | | | 5e. TASK NUMBER | |
| | | | | 5f. WORK UNIT NUMBER WBS 877868.02.07.03.01.03.01 | |
| 7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration John H. Glenn Research Center at Lewis Field Cleveland, Ohio 44135-3191 | | | | 8. PERFORMING ORGANIZATION REPORT NUMBER E-17874 | |
| 9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, DC 20546-0001 | | | | 10. SPONSORING/MONITOR'S ACRONYM(S) NASA | |
| | | | | 11. SPONSORING/MONITORING REPORT NUMBER NASA/TM-2012-217138 | |
| 12. DISTRIBUTION/AVAILABILITY STATEMENT Unclassified-Unlimited Categories: 27, 26, and 23 Available electronically at http://www.sti.nasa.gov This publication is available from the NASA Center for AeroSpace Information, 443-757-5802 | | | | | |
| 13. SUPPLEMENTARY NOTES | | | | | |
| 14. ABSTRACT Thermal barrier coatings will be more aggressively designed to protect gas turbine engine hot-section components in order to meet future rotorcraft engine higher fuel efficiency and lower emission goals. For thermal barrier coatings designed for rotorcraft turbine airfoil applications, further improved erosion and impact resistance are crucial for engine performance and durability, because the rotorcraft are often operated in the most severe sand erosive environments. Advanced low thermal conductivity and erosion-resistant thermal barrier coatings are being developed, with the current emphasis being placed on thermal barrier coating toughness improvements using multi-component alloying and processing optimization approaches. The performance of the advanced thermal barrier coatings has been evaluated in a high temperature erosion burner rig and a laser heat-flux rig to simulate engine erosion and thermal gradient environments. The results have shown that the coating composition and architecture optimizations can effectively improve the erosion and impact resistance of the coating systems, while maintaining low thermal conductivity and cyclic oxidation durability. | | | | | |
| 15. SUBJECT TERMS High toughness thermal barrier coatings; Erosion resistance; Turbine engines life prediction; Thermal conductivity; Cyclic durability | | | | | |
| 16. SECURITY CLASSIFICATION OF: | | | 17. LIMITATION OF ABSTRACT UU | 18. NUMBER OF PAGES 12 | 19a. NAME OF RESPONSIBLE PERSON STI Help Desk (email: help@sti.nasa.gov) |
| a. REPORT U | b. ABSTRACT U | c. THIS PAGE U | | | 19b. TELEPHONE NUMBER (include area code) 443-757-5802 |

